


7929-003-000 Mint/Yellow



安装方式



上下错拼



人字形

所有产品的规格信息由测试样品的平均值推算而出，受产品的生产工艺及内在的差异影响，会存在合理的偏差范围，最终解释权归英特飞模块地毯(中国)有限公司。更多关于产品信息的声明请查看[www.interface.com.cn/page/disclaimer](http://www.interface.com.cn/page/disclaimer)

样式名 BP411 颜色名 Mint/Yellow 系列名 Bike Path

|                  |                                                                                                         |
|------------------|---------------------------------------------------------------------------------------------------------|
| 产品编号             | 7929                                                                                                    |
| 产品规格             |                                                                                                         |
| 产品结构             | Tufted Loop Pile                                                                                        |
| 纱线系统             | 100% Solution Dyed Nylon                                                                                |
| 染色方式             | 100% Solution Dyed                                                                                      |
| 防污               | Protekt <sup>2</sup> ®                                                                                  |
| 抗菌               | Intersept <sup>®</sup>                                                                                  |
| 更多产品规格           |                                                                                                         |
| 簇绒机规格            | 12th Gauge                                                                                              |
| 针密               | 31.5/10cm 8 /in                                                                                         |
| 毯毛厚度             | 2.0 mm±0.5 mm                                                                                           |
| 地毯总厚度            | 5.5 mm±0.5 mm                                                                                           |
| 产品尺寸             | 25*100                                                                                                  |
| 标准底背             | GlasBac <sup>®</sup>                                                                                    |
| 性能指标             |                                                                                                         |
| 应用区域             | Commercial - Heavy Duty                                                                                 |
| 稳定性-剥离强度         | ASTM D3936 ≥ 3.0 lbs/in<br>ISO 11857 ≥ 26 N<br>GB/T 26843 ≥ 26 N                                        |
| 稳定性-尺寸稳定性        | ISO 2551 ≤ 0.1%<br>QB/T 2755 ≤ 0.1%                                                                     |
| 稳定性-簇绒拔出力        | ASTM D1335 ≥ 8.0 lbs<br>ISO 4919 ≥ 30 N<br>QB/T 1090 ≥ 24 N (QB/T 2755)                                 |
| 磨损性 - 脚轮椅        | ISO 4918 ≥ 2.4<br>QB/T 2755 ≤ 0.15%                                                                     |
| 磨损性 - 威特曼鼓轮或六足滚筒 | ASTM D5252 ≥ 3.0 at 12000 cycles<br>ISO 10361 ≥ 3.0 at 22000 cycles<br>GB/T 26844 ≥ 3.0 at 22000 cycles |
| 耐光色牢度            | AATCC 16E ≥ 4 at 60 AFU's<br>ISO 105-B02 ≥ 4-5<br>GB/T 8427 ≥ 4-5                                       |
| 耐摩擦色牢度           | AATCC 165 ≥ 4<br>ISO 105-X12 ≥ 4-5<br>GB/T 3920 ≥ 4-5                                                   |
| 耐水色牢度            | AATCC 107 ≥ 4<br>ISO 105-E01 ≥ 4-5<br>GB/T 5713 ≥ 4-5                                                   |
| 阻燃性 - 乌洛托品(甲胺)测试 | Pass DOC FF 1-70 or ASTM D2859 Test<br>ISO 6925 ≤ 25.4 mm<br>GB/T 11049 ≤ 25.4 mm                       |

|               |                                                                                                                                           |
|---------------|-------------------------------------------------------------------------------------------------------------------------------------------|
| 阻燃性 - 热源辐射测试  | ASTM E648 Class 1<br>ISO 9239-1 B1 CHF $\geq$ 4.5 kW/m <sup>2</sup> (GB 8624)<br>GB/T 11785 B1 CHF $\geq$ 4.5 kW/m <sup>2</sup> (GB 8624) |
| 阻燃性 - 烟气密度    | ASTM E662 < 450<br>ISO 9239-1 $\leq$ 750 %.min (GB 8624)<br>GB/T 11785 s1 $\leq$ 750 %.min (GB 8624)                                      |
| 抗静电性          | AATCC 134 < 3.0 kV<br>ISO 6356 $\leq$ 2.0 kV<br>GB/T 18044 $\leq$ 2.0 kV                                                                  |
| 抗菌处理          | AATCC 174 Parts II & III 99% reduction/No mold 7 Days<br>ASTM E2471 Complete Inhibition                                                   |
| <b>通用测试</b>   |                                                                                                                                           |
| 吸音性           | Absorption Coefficient - NRC 0.0 - 0.2                                                                                                    |
| 动态负载          | ISO 2094 < 15% Thickness loss<br>QB/T 1091 < 15% Thickness loss                                                                           |
| 静态负载          | ISO 3415 < 15% Thickness loss<br>QB/T 1092 < 15% Thickness loss                                                                           |
| 热阻            | ASTM C518 R Value 0.5                                                                                                                     |
| <b>环境指标</b>   |                                                                                                                                           |
| 回收成分含量 %      | 59%                                                                                                                                       |
| 消费前回收         | 57%                                                                                                                                       |
| 消费后回收         | 2%                                                                                                                                        |
| 室内空气质量        | Green Label Plus ASTM D5116 # GLP1354<br>UL GREENGUARD Gold UL 2818 # 71238-420                                                           |
| 产品可持续性        | NSF/ANSI 140 Gold Sustainable Carpet Assessment Standard                                                                                  |
| 成分与生命周期影响     | <a href="#">Environmental Product Declaration - GlasBac®</a>                                                                              |
| 产品寿命末期        | Carpet to Carpet Recycling                                                                                                                |
| 隐含碳排放(从摇篮到大门) | 5.16 kg CO <sub>2</sub> eq./m <sup>2</sup>                                                                                                |
| <b>技术资料</b>   |                                                                                                                                           |
| 安装指南          | <a href="#">View recommended Interface Installation Guidelines online</a>                                                                 |
| 维护指南          | <a href="#">View recommended Interface Maintenance Guidelines online</a>                                                                  |
| 回收再利用         | View details on our ReEntry™ Program                                                                                                      |
| 质保            | <a href="#">15 Year Standard Warranty</a>                                                                                                 |
| 制造工厂          | ISO9001&14001&45001 Certified Plant in Taicang, China                                                                                     |