


1648-002-000 Ocre



Installation Methods



Quarter Turn

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclaimer

Product Viva Colores **Colour** Ocre **Collection**

Product Number	1648
----------------	------

Product Specifications

Product Construction	Tufted Textured Loop
Yarn System	BCF Nylon Type 6.6 - Recycled Nylon
Yarn Manufacturer	Universal
Dye Method	100% Solution Dyed
Soil/Stain Protection	Protekt2®
Preservative Protection	Intersept®

More Product Specifications

Machine Gauge	12th Gauge
Stitches	46/10cm 11.7/in
Pile Thickness	3.0mm ±0.5mm
Total Thickness	6.5mm ±0.5mm
Size Description	50*50
Backing Structure	GlasBac®

Performance Specifications

Stability - Delaminating	ASTM D3936 ≥ 3.0 lbs/in ISO 11857 ≥ 26 N GB/T 26843 ≥ 26 N
Stability - Dimensional Stability	ISO 2551 ≤ 0.1% QB/T 2755 ≤ 0.1%
Stability - Tuft Bind	ASTM D1335 ≥ 8.0 lbs ISO 4919 ≥ 30 N QB/T 1090 ≥ 24 N (QB/T 2755)
Wear - Castor Chair	ISO 4918 ≥ 2.4 QB/T 2755 ≤ 0.15%
Wear - Vetterman Drum	ASTM D5252 ≥ 3.0 at 12000 cycles ISO 10361 ≥ 3.0 at 22000 cycles GB/T 26844 ≥ 3.0 at 22000 cycles
Colour Fastness to Light	AATCC 16E ≥ 4 at 60 AFU's ISO 105-B02 ≥ 4-5 GB/T 8427 ≥ 4-5
Colour Fastness to Rubbing and Crocking	AATCC 165 ≥ 4 ISO 105-X12 ≥ 4-5 GB/T 3920 ≥ 4-5
Colour Fastness to Water	AATCC 107 ≥ 4 ISO 105-E01 ≥ 4-5 GB/T 5713 ≥ 4-5
Flammability - Methanamide Pill	Pass DOC FF 1-70 or ASTM D2859 Test ISO 6925 ≤ 25.4 mm GB/T 11049 ≤ 25.4 mm

Flammability - Radiant Panel	ASTM E648 Class 1 ISO 9239-1 B1 CHF $\geq$ 4.5 kW/m ² (GB 8624) GB/T 11785 B1 CHF $\geq$ 4.5 kW/m ² (GB 8624)
Flammability - Smoke Density	ASTM E662 < 450 ISO 9239-1 $\leq$ 750 %.min (GB 8624) GB/T 11785 s1 $\leq$ 750 %.min (GB 8624)
Antistatic	AATCC 134 < 3.0 kV ISO 6356 $\leq$ 2.0 kV GB/T 18044 $\leq$ 2.0 kV
Lifetime Antimicrobial	AATCC 174 Parts II & III 99% reduction/No mold 7 Days ASTM E2471 Complete Inhibition

Generic Tests

Acoustic – Nylon	Absorption Coefficient - NRC 0.0 - 0.2
Dynamic Loading	ISO 2094 < 15% Thickness loss QB/T 1091 < 15% Thickness loss
Static Loading	ISO 3415 < 15% Thickness loss QB/T 1092 < 15% Thickness loss
Thermal Resistance	ASTM C518 R Value 0.5

Environmental Specifications

Recycled Content %	59%
Pre-Consumer (Total)	57%
Post-Consumer (Total)	2%
Indoor Air Quality	Green Label Plus ASTM D5116 # GLP1354 UL GREENGUARD Gold UL 2818 # 71238-420
NSF Sustainable Carpet	NSF/ANSI 140 Gold Sustainable Carpet Assessment Standard
Ingredients and Life Cycle Impacts	Environmental Product Declaration - GlasBac®
End of Life	Carpet to Carpet Recycling
Embodied Carbon (Cradle to Gate)	5.8 kg CO ₂ eq./m ²

Technical Information

Installation	View recommended Interface Installation Guidelines online
Maintenance	View recommended Interface Maintenance Guidelines online
Reclamation	View details on our ReEntry™ Program
Warranty	15 Year Standard Warranty
Manufacturing Location	ISO9001&14001&45001 Certified Plant in Taicang, China