Textured Woodgrains

Interface®

A004-05 Grey Dune



Installation Methods





All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclamer

NSF Sustainable Carpet

LEED V4

Product Specifications High Performance Luxury Vinyl Tile Wear Layer Thickness 0.55 mm Total Thickness (Metric) 4.5 mm Classification EN 651 Class 33(heavy contract) EN 651 Class 42(light industrial general) Finish CERAMOR™ UV Stabilized Ceramic Bead Coating Acoustic Impact Noise Reduction ISO 140.8 ΔLw = 16dB Nominal Dimensions 25cm x 1m Performance Specifications Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min Size, Tolerance ISO 24342 < 400 mm < 0.25 mm ISO 24342 > 400 mm < 0.35 mm Dimensional Stability ISO 23999 < 0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥ 6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤ 0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 1816	Product Textured Woodgra	ins Colour Grey Dune Collection Level Set
Wear Layer Thickness 0.55 mm Total Thickness (Metric) 4.5 mm Classification EN 651 Class 33(heavy contract) EN 651 Class 42(light industrial general) Finish CERAMOR™ UV Stabilized Ceramic Bead Coating Acoustic Impact Noise Reduction ISO 140.8 ΔLw = 16dB Nominal Dimensions 25cm x 1m Performance Specifications Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min	Product Number	A004
Wear Layer Thickness 0.55 mm Total Thickness (Metric) 4.5 mm Classification EN 651 Class 33(heavy contract) EN 651 Class 42(light industrial general) Finish CERAMOR™ UV Stabilized Ceramic Bead Coating Acoustic Impact Noise Reduction ISO 140.8 ΔLw = 16dB Nominal Dimensions 25cm x 1m Performance Specifications Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min Size, Tolerance ISO 24342 <400 mm <0.25 mm ISO 24342 >400 mm <0.35 mm Dimensional Stability ISO 23999 <0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Product Specifications	
Total Thickness (Metric) Classification EN 651 Class 33(heavy contract) EN 651 Class 42(light industrial general) Finish CERAMOR™ UV Stabilized Ceramic Bead Coating Acoustic Impact Noise Reduction ISO 140.8 ΔLw = 16dB Nominal Dimensions 25cm x 1m Performance Specifications Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min Size, Tolerance ISO 24342 <400 mm <0.25 mm ISO 24342 >400 mm <0.35 mm Dimensional Stability ISO 23999 <0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance Incredients and Life Cycle Incredients and Life Cycle		High Performance Luxury Vinyl Tile
Classification EN 651 Class 33(heavy contract) EN 651 Class 42(light industrial general) Finish CERAMOR™ UV Stabilized Ceramic Bead Coating Acoustic Impact Noise Reduction Nominal Dimensions 25cm x 1m Performance Specifications Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min Size, Tolerance ISO 24342 <400 mm <0.25 mm ISO 24342 >400 mm <0.35 mm Dimensional Stability ISO 23999 <0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005′ with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN ISO 5248 Plass Environmental Specifications	Wear Layer Thickness	0.55 mm
EN 651 Class 42(light industrial general) Finish CERAMOR™ UV Stabilized Ceramic Bead Coating Acoustic Impact Noise Reduction ISO 140.8 ΔLw = 16dB Nominal Dimensions 25cm x 1m Performance Specifications Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min Size, Tolerance ISO 24342 <400 mm <0.25 mm ISO 24342 >400 mm <0.35 mm Dimensional Stability ISO 23999 <0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005′ with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance AD Life Cycle Interedients and Life Cycle	Total Thickness (Metric)	4.5 mm
Acoustic Impact Noise ReductionISO 140.8 ΔLw = 16dBNominal Dimensions25cm x 1mPerformance SpecificationsCritical Heat FluxAS ISO 9239-1 >7kW/m²Smoke RateAS ISO 9239-1 <750%.min	Classification	
Reduction Nominal Dimensions 25cm x 1m Performance Specifications Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min Size, Tolerance ISO 24342 <400 mm <0.25 mm ISO 24342 >400 mm < 0.35 mm Dimensional Stability ISO 23999 <0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Finish	CERAMOR™ UV Stabilized Ceramic Bead Coating
Performance Specifications Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min		ISO 140.8 ΔLw = 16dB
Critical Heat Flux AS ISO 9239-1 >7kW/m² Smoke Rate AS ISO 9239-1 <750%.min Size, Tolerance ISO 24342 <400 mm <0.25 mm ISO 24342 >400 mm < 0.35 mm Dimensional Stability ISO 23999 <0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance Lorredients and Life Cycle	Nominal Dimensions	25cm x 1m
Smoke RateAS ISO 9239-1 <750%.minSize, ToleranceISO 24342 <400 mm <0.25 mm ISO 24342 >400 mm < 0.35 mm	Performance Specifica	tions
Size, Tolerance ISO 24342 < 400 mm < 0.25 mm ISO 24342 > 400 mm < 0.35 mm Dimensional Stability ISO 23999 < 0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥ 6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤ 0.005′ with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Critical Heat Flux	AS ISO 9239-1 >7kW/m²
Size, Tolerance ISO 24342 > 400 mm < 0.35 mm Dimensional Stability ISO 23999 < 0.25% Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥ 6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤ 0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Smoke Rate	AS ISO 9239-1 <750%.min
Thickness ISO 24346 Average value + 0.20mm Resistance to Light ISO 105-B02 ≥6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Size, Tolerance	
Resistance to Light ISO 105-B02 ≥6 Resistance to Heat ASTM F1514 ΔE< 8 avg Max Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Dimensional Stability	ISO 23999 <0.25%
Resistance to Heat Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Thickness	ISO 24346 Average value + 0.20mm
Resistance to Chemicals EN-ISO 26987 Pass Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Resistance to Light	ISO 105-B02 ≥6
Reaction to Fire EN ISO 13501-1 Class BFI-S1 VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Resistance to Heat	ASTM F1514 ΔE< 8 avg Max
VOC Test ISO 10580 Pass Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 <2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Resistance to Chemicals	EN-ISO 26987 Pass
Flexibility ISO 24344 Method A Pass Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Reaction to Fire	EN ISO 13501-1 Class BFI-S1
Static Load ASTM F970 ≤0.005' with 1500 psi Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	VOC Test	ISO 10580 Pass
Castor chair ISO 4918 Pass Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Flexibility	ISO 24344 Method A Pass
Thermal Conductivity EN 12667 0.16 W/mK Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Static Load	ASTM F970 ≤0.005' with 1500 psi
Static Electrical EN 1815 < 2kV Slip Resistance AS 4586:2013 R10 Environmental Specifications	Castor chair	ISO 4918 Pass
Slip Resistance AS 4586:2013 R10 Environmental Specifications Ingredients and Life Cycle	Thermal Conductivity	EN 12667 0.16 W/mK
Environmental Specifications Ingredients and Life Cycle	Static Electrical	EN 1815 < 2kV
Ingredients and Life Cycle	Slip Resistance	AS 4586:2013 R10
Ingredients and Life Cycle	Environmental Specific	cations
Impacts EPD for 4.5mm LVT	Ingredients and Life Cycle Impacts	EPD for 4.5mm LVT

NSF/ANSI 332, Meets Certification Guidelines

Contributes to IEQ: Low Emitting Materials

M&R: EPD and EPR

Recycled Content %	39 %
Embodied Carbon (Cradle to Gate)	9.2 kg CO ₂ eq./m ²
Technical Information	
Installation	See Interface LVT Installation Guidelines online
Maintenance	See Interface LVT Maintenance Guidelines online
Warranty	15 Year Standard LVT Product Warranty