

## 2488-011-000 Cinnabar



## Installation Methods



Ashlar

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see

[www.interface.com.cn/page/disclaimer](http://www.interface.com.cn/page/disclaimer)

**Product** Etch **Colour** Cinnabar **Collection** Coarse Change

Product Number 2488

**Product Specifications**

Product Construction Tufted Textured Loop  
 Yarn System 100% Solution Dyed Nylon  
 Dye Method 100% Solution Dyed  
 Soil/Stain Protection Protakt<sup>2</sup><sup>®</sup>  
 Preservative Protection Intersept<sup>®</sup>

**More Product Specifications**

Machine Gauge 12th Gauge  
 Stitches 49/10cm - 12.45/in  
 Pile Thickness 2.0mm ±0.5mm  
 Total Thickness 5.0mm ±0.5mm  
 Size Description 25\*100  
 Backing Structure GlasBac<sup>®</sup>

**Performance Specifications**

Area of Use Commercial - Heavy Duty  
 Stability - Delaminating ISO 11857 ≥ 26 N  
 GB/T 26843 ≥ 26 N  
 ASTM D3936 ≥ 2.5lbs/in  
 Stability - Dimensional Stability ISO 2551 ≤ 0.1%  
 QB/T 2755 ≤ 0.1%  
 Stability - Tuft Bind ASTM D1335 ≥ 8.0 lbs  
 ISO 4919 ≥ 30 N  
 QB/T 1090 ≥ 24 N (QB/T 2755)  
 Wear - Castor Chair ISO 4918 ≥ 2.4  
 QB/T 2755 ≤ 0.15%  
 Wear - Vetterman Drum ASTM D5252 ≥ 3.0 at 12000 cycles  
 ISO 10361 ≥ 3.0 at 22000 cycles  
 GB/T 26844 ≥ 3.0 at 22000 cycles  
 Colour Fastness to Light AATCC 16E ≥ 4 at 60 AFU's  
 ISO 105-B02 ≥ 4-5  
 GB/T 8427 ≥ 4-5  
 Colour Fastness to Rubbing and Crocking AATCC 165 ≥ 4  
 ISO 105-X12 ≥ 4-5  
 GB/T 3920 ≥ 4-5  
 Colour Fastness to Water AATCC 107 ≥ 4  
 ISO 105-E01 ≥ 4-5  
 GB/T 5713 ≥ 4-5  
 Flammability - Methanamide Pill Pass DOC FF 1-70 or ASTM D2859 Test  
 ISO 6925 ≤ 25.4 mm  
 GB/T 11049 ≤ 25.4 mm

Flammability - Radiant Panel	ASTM E648 Class 1 ISO 9239-1 B1 CHF $\geq$ 4.5 kW/m <sup>2</sup> (GB 8624) GB/T 11785 B1 CHF $\geq$ 4.5 kW/m <sup>2</sup> (GB 8624)
Flammability - Smoke Density	ISO 9239-1 $\leq$ 750 %.min (GB 8624) GB/T 11785 s1 $\leq$ 750 %.min (GB 8624) ASTM E662 Density $\leq$ 450
Antistatic	AATCC 134 < 3.0 kV ISO 6356 $\leq$ 2.0 kV GB/T 18044 $\leq$ 2.0 kV
Lifetime Antimicrobial	AATCC 174 Parts II & III 99% reduction/No mold 7 Days ASTME-2471 Complete Inhibition

### Generic Tests

Acoustic - Nylon	Absorption Coefficient - NRC 0.0 - 0.2
Dynamic Loading	ISO 2094 < 15% Thickness loss QB/T 1091 < 15% Thickness loss
Static Loading	ISO 3415 < 15% Thickness loss QB/T 1092 < 15% Thickness loss
Green Carpet (VOC)	ASTM D5116 Accredited ISO 10580 Accredited
Thermal Resistance	ASTM C518 R Value 0.5

### Environmental Specifications

Recycled Content %	59%
Pre-Consumer (Total)	57%
Post-Consumer (Total)	2%
Indoor Air Quality	Green Label Plus ASTM D5116 # GLP1354 UL GREENGUARD Gold UL 2818 # 71238-420
NSF Sustainable Carpet	NSF/ANSI 140 Gold Sustainable Carpet Assessment Standard
Ingredients and Life Cycle Impacts	<a href="#">Environmental Product Declaration - GlasBac®</a>
End of Life	Carpet to Carpet Recycling
Embodied Carbon (Cradle to Gate)	5.16 kg CO <sub>2</sub> eq./m <sup>2</sup>

### Technical Information

Installation	<a href="#">View recommended Interface Installation Guidelines online</a>
Maintenance	<a href="#">View recommended Interface Maintenance Guidelines online</a>
Reclamation	View details on our ReEntry™ Program
Warranty	<a href="#">15 Year Standard Warranty</a>
Manufacturing Location	<a href="#">ISO9001&amp;14001&amp;45001 Certified Plant in Taicang, China</a>