


2544-002-000 Storm



Installation Methods



Ashlar



Herringbone

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclaimer

Product Works+Fluid **Colour** Storm **Collection** Works+ Series

| | |
|----------------|------|
| Product Number | 2544 |
|----------------|------|

Product Specifications

| | |
|-------------------------|--------------------------|
| Product Construction | Tufted Textured Loop |
| Yarn System | 100% Solution Dyed Nylon |
| Dye Method | 100% Solution Dyed |
| Soil/Stain Protection | Protekt2® |
| Preservative Protection | Intersept® |

More Product Specifications

| | |
|-------------------|------------------|
| Machine Gauge | 12th Gauge |
| Stitches | 40/10cm 10.16/in |
| Pile Thickness | 2.5mm ±0.5mm |
| Total Thickness | 6.5mm ±0.5mm |
| Size Description | 25*100 |
| Backing Structure | GlasBac® |

Performance Specifications

| | |
|---|---|
| Area of Use | Commercial - General Use |
| Stability - Delaminating | ASTM D3936 ≥ 3.0 lbs/in GB/T 26843 ≥ 26 N |
| Stability - Dimensional Stability | QB/T 2755 ≤ 0.1% ISO 2551 ≤ ± 0.1% |
| Stability - Tuft Bind | QB/T 1090 ≥ 24 N (QB/T 2755) ISO 4919 > 30 N |
| Wear - Castor Chair | QB/T 2755 ≤ 0.15% EN 985 > 2.4 Rating @25,000 cycles |
| Wear - Vetterman Drum | GB/T 26844 ≥ 3.0 at 22000 cycles TWC-TM247/251/284 Colour: ≥3 & Structure: ≥3 |
| Colour Fastness to Light | GB/T 8427 ≥ 4-5 AATCC 16 Part 3 ≥ 4 @ 60 Hours |
| Colour Fastness to Rubbing and Crocking | GB/T 3920 ≥ 4-5 AATCC 165 ≥ 4 (Wet & Dry) |
| Colour Fastness to Water | AATCC 107 ≥ 4 GB/T 5713 ≥ 4-5 |
| Flammability - Methanamide Pill | GB/T 11049 ≤ 25.4 mm ASTM 2859 - 7 of 8 passing |
| Flammability - Radiant Panel | GB/T 11785 B1 CHF ≥ 4.5 kW/m ² (GB 8624) ASTM E648 > .45 watts/sq. cm |
| Flammability - Smoke Density | ASTM E662 < 450 GB/T 11785 s1 ≤ 750 %.min (GB 8624) |

| | |
|------------------------|---|
| Antistatic | AATCC 134 < 3.0 kV GB/T 18044 ≤ 2.0 kV |
| Lifetime Antimicrobial | AATCC 174 Parts II & III 99% reduction/No mold 7 Days ASTM E2471 Complete Inhibition |

Generic Tests

| | |
|--------------------|---|
| Acoustic - Nylon | Absorption Coefficient - NRC 0.0 - 0.2 |
| Dynamic Loading | ISO 2094 < 15% Thickness loss QB/T 1091 < 15% Thickness loss |
| Static Loading | ISO 3415 < 15% Thickness loss QB/T 1092 < 15% Thickness loss |
| Green Carpet (VOC) | ASTM D5116 Accredited ISO 10580 Accredited |
| Thermal Resistance | ASTM C518 R Value ≥ 0.5 |

Environmental Specifications

| | |
|------------------------------------|---|
| Recycled Content % | 46% |
| Pre-Consumer (Total) | 45% |
| Post-Consumer (Total) | 1% |
| Indoor Air Quality | Green Label Plus ASTM D5116 # GLP1354 UL GREENGUARD Gold UL 2818 # 71238-420 |
| NSF Sustainable Carpet | NSF/ANSI 140 Gold Sustainable Carpet Assessment Standard |
| Ingredients and Life Cycle Impacts | Environmental Product Declaration - GlasBac® |
| End of Life | Carpet to Carpet Recycling |
| Embodied Carbon (Cradle to Gate) | 5.67 kg CO ₂ eq./m ² |

Technical Information

| | |
|------------------------|---|
| Installation | View recommended Interface Installation Guidelines online |
| Maintenance | View recommended Interface Maintenance Guidelines online |
| Reclamation | View details on our ReEntry™ Program |
| Warranty | 15 Year Standard Warranty |
| Manufacturing Location | ISO9001&14001&45001 Certified Plant in Taicang, China |