## Open Air 404 Transition

## Interface

## 9706-003-000 Nickel Clementine



Installation Methods



All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclamer

## Product Open Air 404 Transition Colour Nickel Clementine Collection Open Air Product Number 9706 **Product Specifications Product Construction Tufted Textured Loop** Yarn System 100% Recycled Solution Dyed Nylon Dye Method 100% Solution Dyed Soil/Stain Protection Protekt2® Preservative Protection Intersept<sup>®</sup> **More Product Specifications** Machine Gauge 12th Gauge Stitches 35/10cm 8.89/in **Pile Thickness** 2.5mm ±0.5mm **Total Thickness** 6.0mm ±0.5mm Size Description 50\*50 GlasBac® **Backing Structure Performance Specifications** Area of Use Commercial - Heavy Use ASTM D3936 ≥ 3.0 lbs/in Stability - Delaminating GB/T 26843 ≥ 26 N Stability - Dimensional $QB/T 2755 \le 0.1\%$ Stability $ISO 2551 \le \pm 0.1\%$ QB/T 1090 ≥ 24 N (QB/T 2755) Stability - Tuft Bind ISO 4919 > 30 N QB/T 2755 ≤ 0.15% Wear - Castor Chair EN 985 > 2.4 Rating @25,000 cycles GB/T 26844 ≥ 3.0 at 22000 cycles Wear - Vetterman Drum ISO 10361(ASTM D5417) ≥ 3.5 Rating @20,000 cycles GB/T 8427 ≥ 4-5 Colour Fastness to Light AATCC 16 Part 3 ≥ 4 @ 60 Hours Colour Fastness to Rubbing GB/T 3920 ≥ 4-5 and Crocking AATCC 165 $\geq$ 4 (Wet & Dry) AATCC 107 ≥ 4 Colour Fastness to Water GB/T 5713 ≥ 4-5 Flammability - Methanamile GB/T 11049 ≤ 25.4 mm Pill ASTM 2859 - 7 of 8 passing GB/T 11785 B1 CHF≥ 4.5 kW/m<sup>2</sup> (GB 8624) Flammability - Radiant Panel ASTM E648 > .45 watts/sq. cm

Flammability - Smoke Density	ASTM E662 < 450 GB/T 11785 s1 ≤ 750 %.min (GB 8624)
Antistatic	AATCC 134 < 3.0 kV GB/T 18044 ≤ 2.0 kV
Lifetime Antimicrobial	AATCC 174 Parts II & III 99% reduction/No mold 7 Days ASTM E2471 Complete Inhibition
Generic Tests	
Acoustic – Nylon	Absorption Coefficient - NRC 0.0 - 0.2
Dynamic Loading	ISO 2094 < 15% Thickness loss QB/T 1091 < 15% Thickness loss
Static Loading	ISO 3415 < 15% Thickness loss QB/T 1092 < 15% Thickness loss
Green Carpet (VOC)	ASTM D5116 Accredited ISO 10580 Accredited
Thermal Resistance	ASTM C518 R Value ≥ 0.5
<b>Environmental Specific</b>	ations
Recycled Content %	62%
Pre-Consumer (Total)	53%
Post-Consumer (Total)	9%
Indoor Air Quality	Green Label Plus ASTM D5116 # GLP1354 UL GREENGUARD Gold UL 2818 # 71238-420
NSF Sustainable Carpet	NSF/ANSI 140 Gold Sustainable Carpet Assessmer Standard
Ingredients and Life Cycle Impacts	Environmental Product Declaration - GlasBac <sup>®</sup>
End of Life	Carpet to Carpet Recycling
Embodied Carbon (Cradle to Gate)	5.67 kg CO <sub>2</sub> eq./m <sup>2</sup>
Technical Information	
Installation	View recommended Interface Installation Guidelines online
Maintenance	View recommended Interface Maintenance Guideline online
Reclamation	View details on our ReEntry <sup>™</sup> Program
Warranty	15 Year Standard Warranty
Manufacturing Location	ISO9001&14001&45001 Certified Plant in