


7621-005-000 Clementine



Installation Methods



Ashlar



Herringbone

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclaimer

Product HN830 **Colour** Clementine **Collection** Human Nature

Product Number 7621

Product Specifications

Product Construction Tufted Cut Pile

Yarn System 100% Recycled Solution Dyed Nylon

Dye Method 100% Solution Dyed

Soil/Stain Protection Protpekt²®

Preservative Protection Intersept[®]

More Product Specifications

Machine Gauge 5/32 in

Stitches 9.00 /in 36.00 ends/10cm

Pile Thickness 7.5mm ±0.5mm

Total Thickness 11.5mm ±0.5mm

Size Description 25*100

Backing Structure GlasBac[®]

Performance Specifications

Area of Use Commercial - General Use

Stability - Delaminating AS/NZS 2111.16 ≥ 50 Newtons
ASTM D3936 ≥ 2.5lbs/in
ISO2551 ≤ 0.1%

Stability - Dimensional Stability ISO 2551 ≤ 0.1%
ISO 2551 ≤ 0.2%
ISO/PAS 17984 < 0.2%

Stability - Tuft Bind ASTM D1335 ≥ 8.0 lbs
ISO 4919 ≥ 30 N
AS/NZS 2111.15 >30 Newtons

Wear - Castor Chair ISO 4918 ≥ 2.4
BS-EN 985 r ≥ 2.4

Wear - Vetterman Drum ISO 10361 ≥ 3-4

Colour Fastness to Light ISO 105-B02 ≥ 4-5
AS2001 1.4.21 ≥ 4
AATCC 16E ≥ 4

Colour Fastness to Rubbing and Crocking AATCC 165 ≥ 4
ISO 105-X12 ≥ 4-5
AS/NZS2111.19.1 ≥ 4

Colour Fastness to Water AATCC 107 ≥ 4
ISO 105-E01 ≥ 4-5
AS2001.4.21 ≥ 4

Flammability - Methanamide Pill Pass DOC FF 1-70 or ASTM D2859 Test
ISO 6925 ≤ 25.4 mm
GB/T 11049 ≤ 25.4 mm

Flammability - Radiant Panel	ASTM E648 Class 1 ISO 9239-1 B1 ASTM E648 Class 2 ISO 9239-1 B2
Flammability - Smoke Density	ASTM E662 Density \leq 450 ISO 9239-1 Density \geq 750
Antistatic	AATCC 134 < 3000 Volts BS ISO 6356 \leq 2.0Kv
Lifetime Antimicrobial	AATCC 171 Washed ASTME-2471 Complete Inhibition AATCC174 Parts 2 & 3 99% reduction. No mold 7 Days

Generic Tests

Acoustic - Nylon	Absorption Coefficient - NRC \geq 0.10
Dynamic Loading	AS/NZS 2111.2 < 12.5% loss ISO 2094 \geq 85
Static Loading	AS/NZS2111.13 < 6% Loss ISO 015/3415 Thickness after 60 mins recovery >85%
Green Carpet (VOC)	ASTM D5116 Accredited ISO 015/3415 Thickness after 60 mins recovery \geq 85%
Thermal Resistance	ASTM C518 R Value \geq 0.5

Environmental Specifications

Recycled Content %	74%
Pre-Consumer (Total)	56%
Post-Consumer (Total)	18%
Indoor Air Quality	Green Label Plus #GLP0820 CDPH 01350
NSF Sustainable Carpet	NSF/ANSI 140 Gold Sustainable Carpet Assessment Standard
Ingredients and Life Cycle Impacts	Environmental Product Declaration - GlasBac®
End of Life	Carpet to Carpet Recycling
Embodied Carbon (Cradle to Gate)	8.74 kg CO ₂ eq./m ²

Technical Information

Installation	View recommended Interface Installation Guidelines online
Maintenance	View recommended Interface Maintenance Guidelines online
Reclamation	View details on our ReEntry™ Program
Warranty	15 Year Standard Warranty
Manufacturing Location	ISO 9001 & 14001 Certified facilities in Troup Country, Georgia, United States